

SLIP RESISTANCE TEST REPORT

Client: Tile Warehouse
Client's Reference: 899489

Tested By: Dave Cockerton
Date: 07 May 2015

DESCRIPTION OF SAMPLE

Manufacturer: Del Conca
Common Name: Natural Nebraska HNT-5
Specimen Size: 600 x 600mm
No. of Specimens Tested. 5

Material Type: Porcelain
Surface Type: Structured
Colour: Nebraska HNT-5
Surface Coating: Nil

METHOD

Tests were carried out in accordance with AS/NZS 4586:2004 (Incorporating Amendment No 1) Slip Resistance of Pedestrian Surfaces, Part 1- Requirements, Appendix A "Method for the Measurement of the Coefficient of friction of Wet Surfaces".

Type of Test: **Wet**

Location of Test: 19b Neil Park Drive

Air Temperature: °C20

East Tamaki

RESULTS

Specimen No.	Dilution Ratio	Dwell Time	Mean Coefficient of Friction
one			0.39
two			0.41
three			0.39
four			0.36
five			0.37

SAMPLE MEAN COEFFICIENT OF FRICTION: 0.39

REQUIREMENTS

Horizontal Surfaces: When tested in accordance with the method set out in Appendix A, the pedestrian surface shall have a mean coefficient of friction of not less than **0.40** and no specimen in that sample shall be less than **0.35**.

COMMENTS:

SAFETY STEP (NZ) LTD

THE ULTIMATE IN ANTI-SLIP AND WAY FINDING SYSTEMS